

# TECHNICAL DATA SHEET

**Product:** Alpha-Flow® Light Cure Flowable Composite

**Product Description:** Alpha-Flow is a radiopaque fluoride containing light cure resin-based micro-hybrid flowable composite. The organic matrix is based on Bis-GMA resin and contains a 38% by volume blend of inorganic fillers with particle sizes ranging from 0.02 – 0.70 microns. This special combination provides a material with extreme versatility for use in a wide range of procedures, including Class III and V cavity figurations and small Class I and II restorations.

**Indications for Use:** For blocking out small undercuts, fill tunnel preps, marginal defect repairs, repair composite and ceramic veneers and re-conform temporary restorations.

**Appearance:** Opaque, flowing paste.  
Shades: A1, A2, A3, A3.5, B1, B2, and Universal Opaquer

**Curing Mechanism:** Light cured by applying an external energy activated Dental Blue Light with minimum output of 600 mW/cm<sup>2</sup> and wavelength 400 to 500 nanometers.

**Shelf-Life:** 30 months

**Filler Type:** Radio-opaque barium-alumino-boro-fluorosilicate glass

Filler % by Volume: 38  
Filler Particle Range (µm): 0.02 – 0.70  
Average Filler Particle Size (µm): 0.65

## Main Composition (%w/w):

Component:	% w/w
Inorganic filler	55 – 65
Blend of methacrylate and dimethacrylate monomers	35 – 45
Initiators	<1
Inhibitor	<1
UV stabilizers	<1
Colorants	<1

## Physical /Mechanical Properties:

Sensitivity to ambient light:	No change in consistency after 60 sec. exposure to test light.
Flexural strength, MPa:	110 (typical value)
Water absorption, µg/mm <sup>3</sup> :	17 (typical value)
Water solubility, µg/mm <sup>3</sup> :	1.3 (typical value)
Shade:	Matches Vita Shade Guide
Color stability:	Stable
Radio-opacity, 1 mm disk:	≥1 mm thickness of Aluminum
Depth of Cure, mm/2:	
Light Shades (A1, A2, A3, B1, B2)	2.3 (typical value)
Dark Shades (A3.5, Opaquer)	2.0 (typical value)

## DENTAL TECHNOLOGIES, INC.

6901 N. HAMLIN AVENUE  
LINCOLNWOOD, ILLINOIS 60712 USA

1.800.835.0885 TOLL FREE [US/CANADA]  
1.847.677.5500 PHONE  
1.847.677.5502 FAX